



Tytane 114
EPDM waterproofing membrane
Thickness 1.14 mm

EN 13956

Use under ballast, mechanically fixed or fully adhered

EN 13967

Application A and T

External fire resistance	EN 13501-5	F _{roof} (t1)
Reaction to fire	EN 13501-1	E
Watertightness (60 kPa)	EN 1928	Pass
Tensile strength (both directions)	EN 12311-2	≥ 8 MPa
Elongation (both direction)	EN 12311-2	≥ 300%
Resistance to impact	EN 12691	≥ 200 mm
Resistance to static loading	EN 12730	≥ 25 kg
Tear resistance	EN 12310-2	≥ 20 N
Joint shear resistance	EN 12317-2	≥ 200 N/50 mm
Peel shear resistance	EN 12316-2	≥ 25 N/50 mm
Root resistance	EN 13948	NPD
Durability (1000 h, UV)	EN 1297	Pass
Watertightness durability	EN 1296/EN 1928	Pass
Cold folding	EN 495-5	≤ -30 °C